


SPECIFICATION FOR APPROVAL

1.Material

Production:	Si-Fe Cores
KDM.P/N:	KSF250-040A-E18
AL:	92(nH/N ²) ± 8%
Material:	40 μ
Coating Color:	Blue
Coating material:	epoxy
Coating Breakdown Voltage:	1000V, 0.5mA, 2Sec




2.Physical Characteristics

Before Coating			After Coating			Le(cm)	Ae(cm ²)	V(cm ³)	W(cm ²)	Weight (g) (ref.)	Box Quantity (Pieces)
OD(Max.) in/mm	ID(Min.) in/mm	Ht(Max.) in/mm	OD(Max.) mm	ID(Min.) mm	Ht(Max.) mm						
2.441 62.00	1.283 32.60	0.709 18.00	63.10	31.37	19.27	14.370	2.646	38.023	7.725	265.2	52


3.Electrical Parameters(Typical) Temperature(25℃ ± 2℃)

Test Item	Test Condition	Value(Typical)	Test Instrument
Inductance	φ 1.2mm/76Ts, 20kHz/1V, I=0A (Evenly full windings)(均匀绕满)	531.4 μH ± 8%	CH3302
DC-Bias	φ 1.2mm/76Ts, 20kHz/1V, I=15A(H=100Oe) (Evenly full windings)(均匀绕满)	410.7 μH (Min.)	WK3255B+WK3265B
	φ 1.2mm/76Ts, 20kHz/1V, I=30A(H=200Oe) (Evenly full windings)(均匀绕满)	293.3 μH (Min.)	
Core Loss	50kHz/1000Gs	800mW/cm ³ (Max.)	SY-8219
Remarks	Set the internal resistance of LCR meter to 100 Ω. (电感测试仪内阻设置100 Ω)		

Core Loss Curves(Typical)



DC-Bias Curves(Typical)



KDM确认栏
KDM
Signature

科达磁电
技术部

客户确认栏
Customer
Signature

请在5个工作日内回签承认书，否则此承认书将作为后续订单的OQC标准。若有疑问，请及时联系我司RD部门。
Please sign back after approval within 5 working days, otherwise this approval sheet would be taken as OQC standard for subsequent orders. If you have any questions, please contact RD department in time.